



Our Ref. : NT/103223/18-03

Page No: 1 of 1

Report No: NDT/RT/180169-03/18

RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client :	Recron (M) Sdn Bhd	Procedure No:	NT/RT/ASME Rev. 7.0
Project :	Dosing System Project	IQI type :	ASTM 1B
Material:	Carbon Steel	Film Manufacturer/Type :	FUJI 100(class II)
Welding Process :	GTAW	Density :	2.0 - 3.5
Examination Code :	ASME V	Sensitivity:	0.33mm(5 wires visible)
Acceptance Code:	ASME B31.3	Source to Object Distance :	400mm
Examination Date:	12 March 2018	Source Side of Object to Film Distance:	(48.3)mm
		No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	DWDI
		Film Viewing Technique :	Double Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
P - 3 4G	10.14	3	48.3	7.14	X	LF	Reject	
					Y	LF	Reject	
					Z	LF	Reject	
P - 4 4G	10.14	3	48.3	7.14	X	Inc	Reject	
					Y	Por	Reject	
					Z	Inc	Reject	

End of Report

Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

Personnel Particulars

Radiographer : Emirsham - NDT Lev. II

Interpreted & Evaluated By: Amat Hamidi - NDT Lev. II

Date: 13 March 2018



Client Representative:

Name:

Date:



Our Ref.: NT/103223/18-03

Page No: 1 of 1

Report No: I NDT/RT/180169-02/18

RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client :	Recron (M) Sdn Bhd	Procedure No:	NT/RT/ASME Rev. 7.0
Project :	Dosing System Project	IQI type :	ASTM 1B
Material:	Carbon Steel	Film Manufacturer/Type :	FUJI 100(class II)
Welding Process :	GTAW	Density :	2.0 - 3.5
Examination Code :	ASME V	Sensitivity:	0.33mm(5 wires visible)
Acceptance Code:	ASME B31.3	Source to Object Distance :	400mm
Examination Date:	12 March 2018	Source Side of Object to Film Distance:	(48.3)mm
		No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	DWDI
		Film Viewing Technique :	Double Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
P - 1 4G	10.14	3	48.3	7.14	X	Por	Accept	
					Y	LF	Reject	
					Z	LF	Reject	

End of Report

Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

Personnel Particulars

Radiographer : Emirsham - NDT Lev. II

Interpreted & Evaluated By: Amat Hamidi - NDT Lev.II

Date: 13 March 2018



Client Representative:

Name:

Date:



Our Ref. : NT/103223/18-03

Page No: 1 of 1

Report No: I NDT/RT/180169-01/18

RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client :	Recron (M) Sdn Bhd	Procedure No:	NT/RT/ASME Rev. 7.0
Project :	Dosing System Project	IQI type :	ASTM 1B
Material:	Carbon Steel	Film Manufacturer/Type :	FUJI 100(class II)
Welding Process :	GTAW	Density :	2.0 - 3.5
Examination Code :	ASME V	Sensitivity:	0.33mm(5 wires visible)
Acceptance Code:	ASME B31.3	Source to Object Distance :	400mm
Examination Date:	12 March 2018	Source Side of Object to Film Distance:	(48.3)mm
		No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	DWDI
		Film Viewing Technique :	Double Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
P - 2 4G	10.14	3	48.3	7.14	X	NRI	Accept	
					Y	NRI	Accept	
					Z	NRI	Accept	

End of Report

Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

Personnel Particulars

Radiographer : Emirsham - NDT Lev. II

Interpreted & Evaluated By: Amat Hamidi - NDT Lev.II

Date: 13 March 2018



Client Representative:

Name:
Date: