



Our Ref.: NT/103510/18-04

Page No: 1 of 1

Report No: NDT/RT/180398-02/18

RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client :	Tenaga Tiub Sdn Bhd	Procedure No:	NT/RT/ASME Rev 6.0
Project :	Lean Solution Cooler	IQI type :	ASTM 1B
Job No:	TT 17195	Film Manufacturer/Type :	FUJI 100(classII)
Material:	SA 516 GR70	Density :	2.2-3.8
Welding Process :	GTAW / SMAW	Sensitivity:	0.33mm(5 wires visible)
Examination Code :	ASME V	Source to Object Distance :	400mm
Acceptance Code:	ASME Sect. VIII DIV.1 : 2015 Ed.+Tema 9TH Ed.	Source Side of Object to Film Distance:	(25.4+3)mm
Examination Date:	13 April 2018	No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	SWSI
		Film Viewing Technique :	Single Wall Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
E-015-06 APWHT								
LS3 (WN89)	28.4	3	—	25.4	0 - 1	NRI	Accept	AR
					1 - 2	Inc	Accept	
					2 - 3	NRI	Accept	
					3 - 4	Inc	Accept	

End of Report

Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

Personnel Particulars

Radiographer : Emirsham - NDT Lev. II
 Interpreted & Evaluated By: Amat Hamidi - NDT Lev.II
 Date: 14 April 2018



Client Representative:
 Name:
 Date:



Our Ref. : NT/103510/18-04

Page No: 1 of 1
 Report No: NDT/RT/180398-04/18

RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client :	Tenaga Tiub Sdn Bhd	Procedure No:	NT/RT/ASME Rev 6.0
Project :	Lean Solution Cooler	IQI type :	ASTM 1B
Job No:	TT 17195	Film Manufacturer/Type :	FUJI 100(classII)
Material:	SA 516 GR70	Density :	2.2-3.8
Welding Process :	GTAW / SMAW	Sensitivity:	0.33mm(5 wires visible)
Examination Code :	ASME V	Source to Object Distance :	400mm
Acceptance Code:	ASME Sect. VIII DIV.1 : 2015 Ed.+Tema 9TH Ed.	Source Side of Object to Film Distance:	(25.4+3)mm
Examination Date:	13 April 2018	No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	SWSI
		Film Viewing Technique :	Single Wall Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

Radiographic Examination Result

Weld Reference (Welder No)	WT	RT	Pipe Diameter	Material Thickness	Film Position	Film Interpretation	Result	Remarks
	(mm)	(mm)	(mm)	(mm)				
E-015-06 APWHT								
LS4 (WN356)	28.4	3	-	25.4	0 - 1	NRI	Accept	
					1 - 2	NRI	Accept	
					2 - 3	NRI	Accept	
					3 - 4	NRI	Accept	
					4 - 5	Por	Accept	
					5 - 6	NRI	Accept	
					6 - 7	NRI	Accept	
					7 - 8	NRI	Accept	
					8 - 9	NRI	Accept	

End of Report

Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

Personnel Particulars

Radiographer : Emirsham - NDT Lev. II
 Interpreted & Evaluated By: Amat Hamidi - NDT Lev. II
 Date: 14 April 2018



Client Representative:
 Name:
 Date: