



Our Ref.: NT/103521/18-05

Page No: 1 of 1

Report No: BFTT/RT-83/18

## RADIOGRAPHIC EXAMINATION REPORT

### Client and Testing Particulars

Client :	Bukit Fraser Thermal Technology Sdn Bhd	Procedure No:	NT/RT/ASME Rev 6.0
Project :	Petronas Chemicals Polyethylene Sdn Bhd Fabrication Of Moisture And Alcohol Removal.	IQI type :	ASTM 1B
Job No:	BFTT 17-634	Film Manufacturer/Type :	FUJI 100/class II
Material:	SA 516 GR 70N	Density :	2.0 - 4.0
Welding Process :	SMAW / SAW	Sensitivity:	0.33mm(5 wires visible)
Examination Code :	ASME V	Source to Object Distance :	1000mm
Acceptance Code:	ASME Sec VIII Div.2 2015 Ed.	Source Side of Object to Film Distance:	(31.8+3)mm
Examination Date:	15 April 2018	No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	SWSI
		Film Viewing Technique :	Single Wall Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

### Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
PE-0-D-902B APWHT								
CS - 3 RS (WN216)	34.8	3	2000	31.8	9 - 10	NRI	Accept	

\_\_\_\_\_ End Of Report \_\_\_\_\_

**Legend:**

TI : Tungsten Inclusion	NRI : No Relevant Indication	Uc : Undercut	Por : Porosity	WT : Weld Thickness
SI : Slag Inclusion	LP : Lack of Penetration	Con : Concavity	BT : Burn Through	RT : Reinforcement Thickness
LF : Lack of Fusion	EP : Excess Penetration	AR : Artifact	Sur : Surface	

**Personnel Particulars**

Radiographer : Emirsham - NDT Lev. II

Client Representative:

Interpreted & Evaluated By: Amat Hamidi - NDT Lev. II

Name:

Date: 16 April 2018

Date:





Our Ref.: NT/103521/18-05

Page No: 1 of 1  
 Report No: BFTT/RT-84/18

## RADIOGRAPHIC EXAMINATION REPORT

### Client and Testing Particulars

Client :	Bukit Fraser Thermal Technology Sdn Bhd	Procedure No:	NT/RT/ASME Rev 6.0
Project :	Petronas Chemicals Polyethylene Sdn Bhd Fabrication Of Moisture And Alcohol Removal.	IQI type :	ASTM 1B
Job No:	BFTT 17-634	Film Manufacturer/Type :	FUJI 100/class II
Material:	SA 516 GR 70N	Density :	2.0 - 4.0
Welding Process :	SMAW / SAW	Sensitivity:	0.33mm(5 wires visible)
Examination Code :	ASME V	Source to Object Distance :	400mm
Acceptance Code:	ASME Sec VIII Div.2 2015 Ed.	Source Side of Object to Film Distance:	(31.8+3)mm
Examination Date:	15 April 2018	No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	SWSI
		Film Viewing Technique :	Single Wall Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

### Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
PE-0-D-902B APWHT								
LS - 1 (WN216)	34.8	3	—	31.8	0 - 1	NRI	Accept	
					1 - 2	NRI	Accept	
					2 - 3	NRI	Accept	
					3 - 4	NRI	Accept	
					4 - 5	NRI	Accept	
					5 - 6	NRI	Accept	
					6 - 7	NRI	Accept	
					7 - 8	NRI	Accept	

End Of Report

#### Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uo: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

### Personnel Particulars

Radiographer : Emirsham - NDT Lev. II

Interpreted & Evaluated By: Amat Hamidi - NDT Lev.II

Date: 16 April 2018



Client Representative:

Name:

Date:



Our Ref.: NT/103521/18-05

Page No: 1 of 1  
 Report No: BFTT/RT-85/18

## RADIOGRAPHIC EXAMINATION REPORT

### Client and Testing Particulars

Client :	Bukit Fraser Thermal Technology Sdn Bhd	Procedure No:	NT/RT/ASME Rev 6.0
Project :	Petronas Chemicals Polyethylene Sdn Bhd	IQI type :	ASTM 1B
Job No:	BFTT 17-634	Film Manufacturer/Type :	FUJI 100/class II
Material:	SA 516 GR 70N	Density :	2.0 - 4.0
Welding Process :	SMAW / SAW	Sensitivity:	0.33mm(5 wires visible)
Examination Code :	ASME V	Source to Object Distance :	400mm
Acceptance Code:	ASME Sec VIII Div.2 2015 Ed.	Source Side of Object to Film Distance:	(31.8+3)mm
Examination Date:	15 April 2018	No of Radiograph(exposure) :	Single Exposure
		No. of Film Each Cassette :	1 Film
		Radiographic Technique :	SWSI
		Film Viewing Technique :	Single Wall Viewing
		Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

### Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
PE-0-D-902B APWHT								
LS - 2 (WN216)	34.8	3	—	31.8	0 - 1	Por	Accept	
					1 - 2	NRI	Accept	
					2 - 3	NRI	Accept	
					3 - 4	NRI	Accept	
					4 - 5	NRI	Accept	
					5 - 6	NRI	Accept	
					6 - 7	NRI	Accept	
					7 - 8	NRI	Accept	

End Of Report

#### Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

### Personnel Particulars

Radiographer : Emirsham - NDT Lev. II

Interpreted & Evaluated By: Amat Hamidi - NDT Lev. II

Date: 16 April 2018

Client Representative:



Name:  
Date:



# NUSANTARA TECHNOLOGIES SDN. BHD. (187753-D)

No. 5, Jalan Anggerik Mokara 31/45, Seksyen 31, Kota Kemuning, 40460 Shah Alam, Selangor Darul Ehsan, Malaysia.

Tel: 03-5122 9766/7/8 Fax: 03-5122 8766/7 E-mail: info@nusatek.com

Our Ref.: NT/103521/18-05

Page No: 1 of 1

Report No: BFTT/RT-86/18

## RADIOGRAPHIC EXAMINATION REPORT

### Client and Testing Particulars

Client :	Bukit Fraser Thermal Technology Sdn Bhd	Procedure No:	NT/RT/ASME Rev 6.0
Project :	Petronas Chemicals Polyethylene Sdn Bhd	IQI type :	ASTM 1B
	Fabrication Of Moisture And Alcohol Removal.	Film Manufacturer/Type :	FUJI 100/class II
Job No:	BFTT 17-634	Density :	2.0 - 4.0
Material:	SA 516 GR 70N	Sensitivity:	0.33mm(5 wires visible)
		Source to Object Distance :	400mm
		Source Side of Object to Film Distance:	(31.8+3)mm
Welding Process :	SMAW / SAW	No of Radiograph(exposure) :	Single Exposure
Examination Code :	ASME V	No. of Film Each Cassette :	1 Film
Acceptance Code:	ASME Sec VIII Div.2 2015 Ed.	Radiographic Technique :	SWSI
		Film Viewing Technique :	Single Wall Viewing
Examination Date:	15 April 2018	Source Type/Size :	Iridium192 (3.2mm)
		Location Markers :	Film Side

### Radiographic Examination Result

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
PE-0-D-902A APWHT								
LS-3 (WN216)	34.8	3	—	31.8	0 - 1	NRI	Accept	
					1 - 2	NRI	Accept	
					2 - 3	NRI	Accept	
					3 - 4	NRI	Accept	
					4 - 5	NRI	Accept	
					5 - 6	NRI	Accept	
					6 - 7	NRI	Accept	
					7 - 8	NRI	Accept	

End Of Report

### Legend:

TI: Tungsten Inclusion	NRI: No Relevant Indication	Uc: Undercut	Por: Porosity	WT: Weld Thickness
SI: Slag Inclusion	LP: Lack of Penetration	Con: Concavity	BT: Burn Through	RT: Reinforcement Thickness
LF: Lack of Fusion	EP: Excess Penetration	AR: Artifact	Sur: Surface	

### Personnel Particulars

Radiographer : Emirsham - NDT Lev. II

Interpreted & Evaluated By: Amat Hamidi - NDT Lev. II

Date: 16 April 2018

Client Representative:

Name:  
Date:





RADIOGRAPHIC EXAMINATION REPORT

Client and Testing Particulars

Client : Bukit Fraser Thermal Technology Sdn Bhd
Project : Petronas Chemicals Polyethylene Sdn Bhd
Job No: BFTT 17-634
Material: SA 516 GR 70N
Welding Process : GTAW / SMAW / SAW
Examination Code : ASME V
Acceptance Code: ASME Sec VIII Div.2 2015 Ed.
Examination Date: 15 April 2018
Procedure No: NT/RT/ASME Rev 6.0
IQI type : ASTM 1B
Film Manufacturer/Type : FUJI 100/class II
Density : 2.0 - 4.0
Sensitivity: 0.33mm(5 wires visible)
Source to Object Distance : 1000mm
Source Side of Object to Film Distance: (31.8+3)mm
No of Radiograph(exposure) : Single Exposure
No. of Film Each Cassette : 1 Film
Radiographic Technique : SWSI
Film Viewing Technique : Single Wall Viewing
Source Type/Size : Iridium192 (3.2mm)
Location Markers : Film Side

Radiographic Examination Result

Table with columns: Weld Reference (Welder No), WT (mm), RT (mm), Pipe Diameter (mm), Material Thickness (mm), Film Position, Film Interpretation, Result, Remarks. Includes entry for PE-0-D-902A APWHT CS-4 (WN090/078) with 10 NRI results.

Legend:

TI : Tungsten Inclusion NRI : No Relevant Indication Uc : Undercut Por : Porosity WT : Weld Thickness
SI : Slag Inclusion LP : Lack of Penetration Con : Concavity BT : Burn Through RT : Reinforcement Thickness
LF : Lack of Fusion EP : Excess Penetration AR : Artifact Sur : Surface

Personnel Particulars

Radiographer : Emirsham - NDT Lev. II
Interpreted & Evaluated By: Amat Hamidi - NDT Lev.II
Date: 16 April 2018

Client Representative:

Name:
Date:





**NUSANTARA TECHNOLOGIES SDN. BHD. (187753-D)**

No. 5, Jalan Anggerik Mokara 31/45, Seksyen 31, Kota Kemuning, 40460 Shah Alam, Selangor Darul Ehsan, Malaysia.

Tel: 03-5122 9766/7/8 Fax: 03-5122 8766/7 E-mail: info@nusatek.com

Our Ref.: NT/103521/18-05

Job No: BFTT 17-634

**Radiographic Examination Result**

Page No: 2 of 2

Report No: BFTT/RT-82/18

Weld Reference (Welder No)	WT (mm)	RT (mm)	Pipe Diameter (mm)	Material Thickness (mm)	Film Position	Film Interpretation	Result	Remarks
PE-0-D-902A APWHT								
CS - 4 (WN090/078)	34.8	3	2000	31.8	10 - 11	NRI	Accept	AR
					11 - 12	NRI	Accept	AR
					12 - 13	NRI	Accept	
					13 - 14	NRI	Accept	
					14 - 15	NRI	Accept	
					15 - 16	NRI	Accept	
					16 - 17	Por	Accept	
					17 - 18	NRI	Accept	
					18 - 19	NRI	Accept	AR
					19 - 20	Por	Accept	AR
					20 - 21	NRI	Accept	
					21 - 22	NRI	Accept	
				22 - 0	NRI	Accept		

End Of Report

